

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 April 2002 (18.04.2002)

PCT

(10) International Publication Number
WO 02/31035 A1

- (51) International Patent Classification⁷: **C08K 5/00**, C08L 23/02, D06L 3/12
- (21) International Application Number: PCT/US01/31112
- (22) International Filing Date: 4 October 2001 (04.10.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 09/689,165 12 October 2000 (12.10.2000) US
- (71) Applicant: **EASTMAN CHEMICAL COMPANY** [US/US]; 100 North Eastman Road, Kingsport, TN 37660 (US).
- (72) Inventors: **IRICK, Gether, Jr.**; 113 South Patrick Drive, Gray, TN 37615 (US). **DAILY, Jeffrey, Daniel**; 404 Winston Circle, Kingsport, TN 37664 (US).
- (74) Agent: **WOOD, Jonathan, D.**; P.O. Box 511, Kingsport, TN 37662-5075 (US).
- (81) Designated States (*national*): BR, CN, JP, MX.
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- Published: — with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 02/31035 A1

(54) Title: MULTI-COMPONENT OPTICALLY BRIGHTENED POLYOLEFIN BLEND

(57) Abstract: A blend of optical brighteners includes (a) from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes; and (b) from 55 to 5 weight % of at least one bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, a coumarin based brightener, and mixtures thereof, wherein the weight percents of the optical brightener blend are based on the total weight of optical brighteners in the blend. The optical brightener blend is useful for admixing with a polyolefin resin which in turn may be used for photo imaging applications.

MULTI-COMPONENT OPTICALLY BRIGHTENED POLYOLEFIN BLEND

BACKGROUND OF THE INVENTION

5 Field of the Invention:

The present invention relates to a mixture of optical brighteners that are useful for brightening polyolefin films. Another aspect of the present invention is for compositions having the mixture of particular optical brighteners included therewith, and particularly to polyolefins having a blend of three (3) optical brighteners wherein two of the optical
10 brighteners are bis-benzoxazolyl stilbenes and the third optical brightener is selected from at least one bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a coumarin based brightener and a pyrazoline based brightener. The polyolefin-brightener blend is particularly useful as a resin coating for a photographic support.

15 Background of the Invention:

Polyolefins are widely used in extrusion and molding applications, and in the making of films for varied applications. For example, polyethylene compositions are used in cast or tubular blown films, thin films, extrusion coated paper, paperboard, photographic paper, digital and thermal imaging papers, diaper backing, plastic
20 substrates, injection or compression molded objects, packaging applications (such as coatings on soap boxes, milk cartons, fruit juice cartons, etc.), and the like. In these applications, the polymer is generally processed at high temperatures.

The present invention has particular utility in the field of extruded films for imaging and photographic support applications, such as, extrusion coated paper, paperboard,
25 photographic paper, digital paper and thermal imaging papers. With respect to a photographic support, generally a paper base material is coated with a thin polyolefin film. The polyolefin coating provides a very smooth surface when thin layers of a silver halide emulsion, are desired to be coated on the photographic paper.

To improve image quality, the polyolefin coating usually includes an optical
30 brightener, such as a fluorescent whitening agent, to make the white areas of the support even brighter. Typical optical brighteners fluoresce upon irradiation with ultraviolet light emitting visible light, typically bluish in hue, replacing the light that would have been lost

-2-

and thereby enhancing the brightness of the support. Optical brighteners for use in such fields as photographic printing materials must absorb ultraviolet light, especially in the region from 280 to 405 nanometers (nm), and re-emit such light so as to enhance the brightness of the print. Desirably, the optical brightener has stability to temperatures as high as 310°C to 330°C, so that it may be incorporated into the polyolefin during an extrusion process or film forming process and in extruding the polyolefin onto the paper based material.

It is desirable that the optical brightener be non-migrating so that it remains in the polyolefin coating and does not exude as a surface film on the polyolefin. Such exudation not only gives rise to a non-uniform brightness of the reflection surface, but also readily transfers to any other surface coming in contact with it. For example, a brightener transferred to the back side of the adjacent support layer when wound in roll can adversely affect subsequent coating and finishing operations of the photograph. This can result in the final product having a poor quality and performance.

It is recognized in the art that the addition of optical brighteners to polyolefins has been less than satisfactory. For example, U.S. Patent 3,449,257 describes 2,5-bis(benzoxazolyl)thiophenes, such as Uvitex OB® available from Ciba Specialty Chemicals, as non-migrating brighteners for hydrophobic polymers, but were found to undergo bleeding and yellowing from a polyolefin film in U.S. Patent No. 5,173,397

In an effort to improve the compatibility between hydrophobic or non-polar polyolefins and optical brighteners, U.S. Patent Nos. 4,794,071 and 4,859,539 issued to Tomko, et al. on December 27, 1988, and August 22, 1989, respectively, disclose a mixture of optical brighteners that when incorporated into a pigmented polyolefin layer of a photographic support minimizes exudation of the brightener at the polyolefin surface.

The mixture of optical brighteners includes three specific fluorescent bis(benzoxazolyl)stilbenes. U.S. Patent No. 4,794,071 teaches that single component optical brighteners of the mixture exhibit severe exudation when compared to the optical brightener mixture described in U.S. Patent No. 4,794,071.

U.S. Patent No. 5,817,448 issued to Hayashi et al. on October 6, 1998 discloses a silver halide photographic material having a support material with at least one light-sensitive silver halide emulsion layer provided thereon. The support material includes a

-3-

resin coated paper having a titanium dioxide pigment coated with a silane coupling agent, and at least one brightening agent selected from a bis-(benzoxazolyl)naphthalene based brightening agent, a bis-(benzoxazolyl)thiophene based brightening agent, a coumarin based brightening agent and a pyrazoline based brightening agent.

5 The patent further discloses a silver halide photographic material having a support material with three kinds of light-sensitive silver halide emulsion layers, with each layer having different light-sensitive wavelength regions. The support material includes a resin coated paper having a titanium dioxide pigment coated with a silane coupling agent, and at least one bis-(benzoxazolyl)stilbene based brightening agent. However, the patent is
10 silent as to using a combination of at least three optical brighteners where two are bis-(benzoxazolyl)stilbene based brightening agents and the third brightening agent is selected from a bis-(benzoxazolyl)naphthalene based brightening agent, a bis-(benzoxazolyl)thiophene based brightening agent, a coumarin based brightening agent and a pyrazoline based brightening agent.

15 U.S. Patent No. 4,416,795 discloses a mixture of optical brighteners having from 1 to 99 weight % of a bis-benzoxazolylstyrene and from 99 to 1 weight % of one or more secondary compounds.

U.S. Patent No. 5,106,989 discloses a photographic support having a polyolefin resin coating wherein the resin includes a titanium dioxide pigment and an alkyl-
20 substituted 2,2-(1,4-naphthalenediyl)dibenzoxazole optical brightener.

U.S. Patent No. 4,363,744 discloses a mixture of optical brighteners wherein a bis-benzoxazolyl or bis-benzothiazolyl-stilbene is mixed with a second mixture of optical brighteners having formulae I and II disclosed therein.

U.S. Patent No. 4,169,810 discloses a mixture of optical brighteners having from
25 0.05 to 0.95 part by weight of a benzoxazolyl- or a benzothiazolyl-stilbene compound and from 0.95 to 0.05 part by weight of a bis-benzoxazolyl- or bis-benzothiazolyl-stilbene compound or a benzoxazolyl- or benzothiazolyl-stilbene oxazolo[5,4-6]pyridinyl or oxazolo[2,3-b]pyridinyl compound.

U.S. Patent No. 4,129,412 discloses a mixture of optical brighteners having 0.05 to
30 1 % of a 4-benzoxazolylstilbene derivative and 1 to 0.05 % of a 1,1-bis-benzoxazolyl or

-4-

bis-benzthiazolyl-naphthalene derivative that are useful for brightening textile material of linear polyesters, polyamides and acetyl cellulose.

Accordingly, there is a need for the incorporation of an optical brightener into a non-polar polyolefin that will exhibit the good compatibility with the polyolefin and not
5 exude as a surface film on the polyolefin.

SUMMARY OF THE INVENTION

Broadly, the present invention is a mixture of optical brighteners that show an
10 enhanced degree of whiteness when admixed with a polyolefin and particularly when admixed with polyethylene to make a film, as compared to the same amount of the constituents in the polyolefin as single components. The optical brightener mixture of the present invention includes (a) of from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes and (b) of from 55 to 5 weight % of at least one bis(benzoxazolyl)naphthalene
15 based brightener, bis(benzoxazolyl)thiophene based brightener, a coumarin based brightener and a pyrazoline based brightener, wherein the weight percents are based on the total weight of optical brighteners in the mixture.

Another aspect of the present invention is for an optically brightened polyolefin resin having admixed therein from 0.001 to 0.1 weight % of the optical brightener
20 mixture described above.

Yet another aspect of the present invention is for a photoimaging material having a photoimaging support material comprised of a paper based material having a pigment comprised of titanium dioxide that is substantially free of siloxanes and a mixture of optical brighteners in accordance with this invention.

25 It is an object of the present invention to provide an optical brightener mixture for a polyolefin resin that is characterized by excellent absorption and emission attributes and has the necessary heat stability to meet the requirements for use in a photoimaging resin coating.

Another object of the present invention is for an optical brightener mixture having a
30 low exudation rate from a polyolefin film, wherein the exudation is determined by the b* CIE value.

-5-

Yet another object of the present invention is to provide a photoimaging support material having a titanium dioxide pigment and an optically brightened, polyolefin resin coating on at least one surface of the support material.

These and other objects and advantages of the present invention will become more
5 apparent to those skilled in the art to which this invention pertains upon reference to the following detailed description of the preferred embodiments.


DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

10 The various aspects of the present invention are particularly described with regard to the preferred embodiments as a blend of optical brighteners that are useful in blending with a polyolefin resin. The optically brightened polyolefin resin is further useful in a photo imaging material having a support material coated on at least one surface with the optically brightened polyolefin. In addition, the blend of optical brighteners and resin
15 incorporating the same are useful in applications where an optically brightened polyolefin coating resistant to brightener exudation is desired.

With regard to the compositional blend of optical brighteners, the blend includes a at least three optical brighteners wherein two are a mixture of benzoxazolyl stilbenes and one is an optical brightener other than a benzoxazolyl stilbene. Specifically, the optical
20 brightener blend includes (a) from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes; and (b) from 55 to 5 weight % of at least one bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, or a coumarin based brightener, and mixtures thereof wherein the weight
25 optical brightener blend includes from 55 to 70 weight % of mixture (a) and from 45 to 30 weight % of constituent (b).


The mixture, (a), of benzoxazolyl stilbenes has as a first component (i), from 10 to 90 parts by weight of a 4,4'-bis(benzoxazol-2-yl)stilbene and, as a second component (ii), from 90 to 10 parts by weight of mono and/or di substituted benzoxazolyl stilbenes
30 represented by the formula:

-6-



wherein $R_1 - R_4$ are independently selected from hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxy group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof. Preferably, $R_1 - R_4$ are independently selected from hydrogen, a methyl group, an ethyl group, a tert-butyl group, a tert-octyl group and mixtures thereof. In a particularly preferred embodiment, the mixture (a) of benzoxazolyl stilbenes includes from 25 to 50 parts by weight of 4,4'-bis(benzoxazol-2-yl)stilbene and (ii) from 75 to 50 parts by weight of a second component selected from 4-(benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene, and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene. Preparation of the mono and di benzoxazolyl stilbenes is described in greater detail in U.S. Patent Nos. 3,260,715 and 4,282,355, the entire disclosures of which are incorporated herein by reference.

The bis(benzoxazolyl)naphthalene based brightening agent is preferably represented by the formula:




15

wherein $R_5 - R_8$ are independently selected from hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxy group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof. Preferably, $R_5 - R_8$ are independently selected from hydrogen, a methyl group, an ethyl group, a tert-butyl group, a tert-octyl group and mixtures thereof. More preferably, the bis(benzoxazolyl)naphthalene based brightening agent is selected from 1,4-bis(benzoxazol-2-yl)naphthalene; 1,4-bis(5-tert-butylbenzoxazol-2-yl)naphthalene; 1,4-bis(5-tert-octylbenzoxazol-2-yl)naphthalene and mixtures thereof.

The bis(benzoxazolyl)thiophene based brightening agent is preferably represented by the formula:


25

-7-




wherein $R_9 - R_{12}$ are independently selected from hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms, and mixtures thereof. Preferably, $R_9 - R_{12}$ are independently selected from hydrogen, a methyl group, an ethyl group, a tert-butyl group, a tert-octyl group, and mixtures thereof. More preferably, the bis(benzoxazolyl)thiophene based brightening agent is selected from 2,5-bis(benzoxazol-2-yl)thiophene; 2,5-bis(5-tert-butylbenzoxazol-2-yl)thiophene; 2,5-bis(5-tert-octylbenzoxazol-2-yl)thiophene and mixtures thereof.

The pyrazoline based brightening agent is preferably represented by the formula:



wherein $R_{13} - R_{15}$ are independently selected from hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms, a sulfonamido group, and mixtures thereof. Preferably, $R_{13} - R_{15}$ are independently selected from hydrogen, a methyl group, an ethyl group, a tert-butyl group, a tert-octyl group, and mixtures thereof. More preferably, the pyrazoline based brightening agent is 1-(4-tert-octylphenyl)-3-phenylpyrazoline.

The coumarin based brightening agent is preferably represented by the formula:



wherein R_{16} is selected from an organic group containing a triazine and triazole ring, R_{17} is selected from hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon

-8-

atoms, and mixtures thereof. More preferably, the coumarin based brightening agent is selected from 3-phenyl-7-(2,3-naphthotriazol-2-yl)coumarin; 3-phenyl-7-(1,2-naphthotriazol-2-yl)coumarin; 3-phenyl-7-(benzotriazol-2-yl)coumarin and mixtures thereof.

5 In a particularly preferred embodiment, the blend of optical brighteners includes (a) from 45 to 95 weight % of a mixture having (i) from 25 to 50 parts by weight of 4,4'-bis(benzoxazol-2-yl)stilbene and (ii) from 75 to 50 parts by weight of a second component (ii) selected from 4-(benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene, and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene and (b) from 55 to 5 weight % of another,
10 non-bis(benzoxazolyl)stilbene selected from 2,5-bis(5-t-butylbenzoxazol-2-yl)thiophene, or coumarin brightener (Leucopure EGM).

The aforementioned bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, a coumarin based brightener are discussed in greater detail in U.S. Patent No. 5,817,448, the entire
15 disclosure of which is incorporated herein by reference.

In another aspect of the present invention, the optical brightener blend described above can be incorporated into a polyolefin. The amount of brightener blend used in the polyolefin is an effective amount to brighten the reflective layer or coating. Such amounts in the polyolefin can be from 0.001 to 0.1 weight % based on the total weight of
20 the polyolefin coating. However, for photoimaging, the amount of the optical brightener blend admixed with the polyolefin is desirably from 0.005 to 0.08 weight %. Excellent brightening with no or minimal exudation has resulted when 0.01 to 0.06 weight % of the blend of optical brightening agents has been incorporated into the polyolefin.

Polyolefinic resins suitable for use with the optical brightener blend and in
25 accordance with the present invention include any coatable polyolefin material known in the photographic art. Representative of these materials are polyethylene, and particularly useful are LDPE, HDPE, and LLDPE, polypropylene, polystyrene, polybutylene, polyolefin copolymers, and mixtures containing one or more homopolymers and/or copolymers thereof. Polyethylenes useful in this invention will generally have densities
30 in a range of 0.900 g/cc to 0.980 g/cc, and preferably from 0.910 to 0.965 g/cc, although lower and higher density polyethylenes may be used. Useful materials will preferably

-9-

also have melt index values of 0.7 to 50g/10 min. The polyolefin composition can also be a mixture of polyolefins, such as a mixture of two or more polyethylenes having different melt indexes. The polyethylenes can contain, and generally will contain, other materials used as processing aids, or materials used to make the finished product more useful in it's
5 end-use.

The polyolefin can be copolymerized with one or more comonomers such as vinyl stearate, vinyl acetate, acrylic acid, methyl acrylate, ethyl acrylate, butyl acrylate, acrylamide, methacrylic acid, methyl methacrylate, ethyl methacrylate, methacrylamide, butadiene, and isoprene. Preferred polyolefins are film forming and cohere to paper.

10 The optical brightener mixture can be incorporated into the polyolefin by conventional methods. Preferred are methods whereby the brightener is uniformly dispersed within the polyolefin. Such methods include a melt extrusion process, a kneading extruder, a roll mill, a high shear mixer, or a twin-screw compounder. Optionally, the brighteners may be added to the polyolefin in the form of powder blend to
15 make a single concentrate in a suitable polymeric resin, or as individual concentrates of the individual brighteners in the polymeric resin.

In accordance with another aspect of the present invention, a photoimaging material is provided having a silver halide emulsion layer coated on a photoimaging support material, a pigment, and coated on at least one surface of the support material, the
20 optically brightened polyolefin resin described above. Desirably the photoimaging support material is a cellulosic material such as a paper base material, or a modified cellulose material selected from cellulose materials that are useful for modification by chemical derivatization on or regeneration and includes, but is not limited to, cellulose esters, cellulose ethers, nitrocellulose, viscose cellulose, microcrystalline cellulose, and
25 microfibrillated cellulose with paper being preferred. The paper base material can also be prepared from a blend of wood cellulose and a suitable synthetic fiber such as a blend of wood cellulose and polyethylene fiber.

The paper base material employed in accordance with the present invention can be any paper base material which has heretofore been considered useful as a photographic
30 support. The weight and thickness of the support can be varied depending on the intended use. A preferred weight range is from 20 g/m² to 500 g/m². Preferred thickness (those

-10-

corresponding to commercial grade photographic paper) ranges from 20 microns to 500 microns. It is preferred to use a paper base material having a smooth surface. The paper base material can be made from any suitable paper stock preferably comprising hard or softwood. Either bleached or unbleached pulp can be utilized as desired.

5 The paper base material may further contain, if desired, agents to increase the strength of the paper such as wet strength resins, e.g., the amino-aldehyde or polyamide-epichlorohydrin resins, and dry strength agents, e.g., starches, including both ordinary starch and cationic starch, or polyacrylamide resins. Other additives include water soluble gums, e.g., cellulose ethers such as carboxymethyl cellulose, sizing agents, e.g., a
10 ketene dimer, sodium stearate which is precipitated onto the pulp fibers with a polyvalent metal salt such as alum, aluminum chloride or aluminum sulfate; fluorescing agents; antistatic agents; fillers, including clays or pigments such as titanium dioxide; dyes; and the like.

 A white pigment can be added to the polyolefin resin layer with the optical
15 brightener mixture. The white pigment can be can be titanium dioxide, zinc oxide, zinc sulfide, zirconium dioxide, white lead, lead sulfate, lead chloride, lead aluminate, lead phthalate, antimony trioxide, white bismuth, tin oxide, white manganese, white tungsten and combinations thereof. The pigment is used in any form that is conveniently dispersed within the polyolefin. The preferred pigment is titanium dioxide that is substantially free
20 of silane coupling agents. As used herein, "substantially free" means less than 0.01 weight % and preferably less than 0.001 weight % of a silane coupling agent. The titanium dioxide can be anatase, rutile or combinations of these forms. The titanium dioxide may further contain oxides of silicon or aluminum, or mixtures thereof, as surface coatings or present inside the titanium dioxide particle as described in US patent nos.
25 5,075,206 and US 5,173,397, the entire disclosures of which are incorporated herein by reference. Other elements such as zinc, calcium and magnesium may also be present in or on the titanium dioxides as a result of their use by the pigment manufacturers to tailor the performance of the pigments for specific end-use applications. Enhanced image resolution in a photographic element can be obtained by the addition of functional
30 amounts of such highly white-light reflective pigments to the polyolefin layer. Preferably, the white pigment is used in the range from 3 to 35%, more preferably 5 to 25% by

weight based on the total weight of the polyolefin coating. Titanium dioxide at levels of 5 to 20% is particularly useful.

In addition to the blend of optical brighteners and the white pigment, the polyolefin coating can contain, if desired, a variety of additives including stabilizers and antioxidants such as 4,4'-butylidene-bis(6-tert-butyl-meta-cresol), di-lauryl-3,3'-thiodipropionate, bis(2,2,6,6-tetramethyl-4-piperidiny)sebacate (TINUVIN 770, available from Ciba Specialty Chemicals), 1,3,5-triazine-2,4,6-triamine, N,N''-[1,2-ethanediylbis[[[4,6-bis[butyl(1,2,2,6,6-pentamethyl-4-piperidiny)amino]-1,3,5-triazine-2-yl]imino]-3,1-propanediyl]]-bis[N',N''-dibutyl-N',N''-bis(1,2,2,6,6-pentamethyl-4-piperidiny)-(CHIMASSORB 119, available from Ciba Specialty Chemicals), 2,2-bis[[3-[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]-1-oxopropoxy]methyl]-1,3-propanediyl 3,5-bis(1,1-dimethylethyl)-4-hydroxybenzenepropanoate (IRGANOX 1010, available from Ciba Specialty Chemicals), octadecyl 3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)propanoate (IRGANOX 1076, available from Ciba Specialty Chemicals), tris(2,4-di-tert-butylphenyl)phosphite (IRGAFOS 168, available from Ciba Specialty Chemicals), and combinations of the above; slip agents, such as higher aliphatic acid metal salts such as magnesium stearate, calcium stearate, zinc stearate, aluminum stearate, sodium stearate, calcium palmitate, sodium palmitate, zirconium octylate, sodium laurate, and mixtures thereof; additional optical brighteners; antistatic agents; dispersing agents; coating aids; lubricants; dyes; and the like, as are well known to those skilled in the art.

The coating of the paper base material with the polyolefin preferably is by extrusion from a hot melt, as is known in the art. The surface of the paper base material desirably is treated with corona discharge to obtain a good adhesion between the polyolefin and the paper before the polyolefin coating is extruded onto the treated surface. The invention can be practiced within a wide range of extrusion temperatures, for example, 150°-350°C. For many applications, preferred extrusion temperatures are from 310°-330°C. As noted, it is an advantageous feature of this invention that the mixture of optical brighteners is stable to such temperatures. Generally, the optically brightened polyolefin coating, over which the silver halide emulsion is applied, is coated onto the paper base material in a coverage of 1 to 100 g/m², at a uniform thickness ranging from about 1 to 100 microns. About the same coverage of clear polyethylene coating preferably is applied to the side of

-12-

the paper base material opposite to the pigmented polyolefin coating. As such, the polyolefin coatings are particularly effective in preventing acid and alkaline photographic processing solutions from penetrating to the paper base.

The photographic elements in accordance with this invention comprise the above-described optically brightened photographic support and at least one silver halide emulsion layer. Any of the known silver halide emulsion layers are useful in preparing photographic elements in accordance with this invention. Generally, the photographic element is prepared by coating the support with one or more layers having a dispersion of silver halide crystals in an aqueous solution of gelatin. The coating process is generally carried out on a continuously operating machine with a single layer or a plurality of layers are applied to the support.

The present invention is illustrated in greater detail by the specific examples presented below. It is to be understood that these examples are illustrative embodiments and are not intended to be limiting of the invention, but rather are to be construed broadly within the scope and content of the appended claims.

In the Examples below, the following optical brighteners were used:

- 4,4'-bis(Benzoxazol-2-yl)stilbene (C)
- 4-(Benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene (D)
- 4,4'-bis(5-Methylbenzoxazol-2-yl)stilbene (E)
- 2,5-bis(5-t-Butylbenzoxazol-2-yl)thiophene (F)
- 3-Phenyl-7-(1,2-naphthotriazol-2-yl)coumarin (Leucopure EGM) (G)

Color measurements (Commission International d'Eclairage $L^*a^*b^*$ values in a Spectroflash 600 unit using D65 illuminant with ultraviolet included, and 10 degree observer) were made on the films prepared as specified below. The films were then aged in a Blue M convection oven at 60°C for up to 88 hours, and at room temperature for up to 24 weeks. The color measurements were thereafter retaken. The change in b^* value was taken as a measure of the rate of exudation of the optical brightener from the film, with the greater the change in b^* the greater the amount of optical brightener exuding from the surface. The larger the numerical value of $-b^*$, the greater the brightening efficiency. Decreases in the numerical value of $-b^*$ during aging indicate a loss of brightening efficiency and an increase in yellowness. Positive values for b^* indicate a

-13-

yellowed resin, and the greater the numerical value for b*, the more yellow the resin will appear.

COMPARATIVE EXAMPLES 1-13

5 A dry-blended mixture of 6.665 pounds (3023.2 grams) of low-density polyethylene, 3.33 pounds (1513.6 grams) of a concentrate containing 33.3 weight % of an anatase titanium dioxide in low-density polyethylene, and the specified amount of optical brightener(s) was added to give the desired brightener concentration. This mixture was melt-blended at 360°F in a single-screw extruder. The extrudate was pelletized and
10 was then extruded at 360°F into 3-mil (75 micron) thick film. Color measurements were taken after the specified time interval and in accordance with the method described above. The results of the yellowness measurements appear in Table I below.

COMPARATIVE EXAMPLES 14 AND 15

15 The specified amount of optical brightener mixture was admixed with the dry-blended mixture of low-density polyethylene, anatase or rutile titanium dioxide of Comparative Examples 1-13. This mixture was melt-blended at 400-450°F in a single-screw extruder. The extrudate was pelletized and was then extruded at 600°F into 3-mil (75 micron) thick film. Color measurements were taken after the specified time interval
20 and in accordance with the method described above. The results of the yellowness measurements appear in Table II below.

EXAMPLES 16 AND 17

In accordance with the present invention, the specified amount of optical brightener
25 mixture was admixed with the dry-blended mixture of low-density polyethylene, anatase or rutile titanium dioxide of Comparative Examples 1-13. This mixture was melt-blended at 400-450°F in a single-screw extruder. The extrudate was pelletized and was then extruded at 600°F into 3-mil (75 micron) thick film. Color measurements were taken after the specified time interval and in accordance with the method described above. The
30 results of the yellowness measurements appear in Table III below.

TABLE 1

Weight Percentages of Brighteners							b*, 60C				b*, 20-22C			
							Ageing for Hours Indicated				Ageing for Wks Indicated			
Example	C	D	E	F	G	TiO2	0	44	88	0	8	24		
1	0.025					Anatase	-7.45	-0.49	-0.61	-7.60	-4.79	-1.48		
2	0.05					Anatase	-8.30	4.22	4.44	-8.29	-0.58	-0.88		
3		0.05				Anatase	-8.32	-3.94	-3.40	-8.34	-5.83	-3.79		
4			0.05			Anatase	-8.47	-3.03	1.39	-8.44	-7.18	-1.36		
5				0.025		Anatase	---	---	---	-4.64	-4.82	-4.96		
6				0.05		Anatase	---	---	---	-6.33	-6.63	-6.82		
7				0.125		Anatase	-9.32	-8.75	-9.16	-9.55	-9.06	-7.60		
8					0.05	Anatase	-7.00	0.36	0.72	-6.89	-0.23	-0.20		
9	0.0025		0.0225			Anatase	-8.31	-5.81	-4.05	-8.33	-7.59	-4.16		
10	0.005		0.0045			Anatase	-11.58	5.55	---	-11.51	-3.29	-3.80		
11	0.0275		0.0225			Anatase	-10.75	-1.47	---	-10.71	-6.44	-1.05		
12	0.013			0.013		Anatase	-6.34	-4.66	-4.02	-6.30	-5.66	-4.39		
13	0.0143		0.0117			Anatase	-7.06	-5.61	-4.83	-7.09	-6.61	-4.71		

TABLE II

Weight Percentages of Brighteners												
							b*, 60C			b*, 20-22C		
							Ageing for Hours Indicated			Ageing for Wks Indicated		
Example	C	D	E	F	G	TiO2	0	44	88	0	8	24
14	0.025		0.025			Anatase	-8.89	-7.40	-6.70	-8.86	-8.86	-8.02
15	0.025		0.025			Rutile	-3.60	-3.50	-3.22	-2.98	-3.01	-2.74

TABLE III

Weight Percentages of Brighteners							b*, 60C			b*, 20-22C		
							Ageing for Hours Indicated			Ageing for Wks Indicated		
Example	C	D	E	F	G	TiO2	0	44	88	0	8	24
16	0.015		0.0225	0.025		Anatase	-9.09	-9.06	-9.40	-8.83	-8.65	-8.28
17	0.015		0.0225	0.025		Rutile	-3.99	-3.97	-4.14	-3.85	-4.06	-4.00

-16-

As can be seen from Table I, Comparative Examples 1-4, a single benzoxazolylstilbene brightener exudes badly upon ageing. Comparative examples 5-7 show that a benzoxazolylthiophene brightener alone does not exude upon ageing, but that it requires much higher concentrations to achieve the same brightening efficiency provided by individual benzoxazolylstilbene brighteners, or by blends containing benzoxazolylstilbene brighteners. Comparative Example 8 shows that a coumarin brightener alone exudes badly upon ageing. Comparative examples 9, 10, 11, 13, 14 and 15 show that combinations of two benzoxazolylstilbene brighteners also exude upon ageing. Comparative example 12 shows that a combination of one benzoxazolylstilbene brightener with a benzoxazolylthiophene brightener also exudes upon ageing.

In accordance with the present invention, as can be seen from Examples 16 and 17, combinations of two benzoxazolylstilbene brighteners with a non-benzoxazolylstilbene brightener show high initial brightening efficiency and no loss of brightening efficiency upon ageing at either room temperature, or at 60°C.

Having described the invention in detail, those skilled in the art will appreciate that modifications may be made to the various aspects of the invention without departing from the scope and spirit of the invention disclosed and described herein. It is, therefore, not intended that the scope of the invention be limited to the specific embodiments illustrated and described but rather it is intended that the scope of the present invention be determined by the appended claims and their equivalents.


CLAIMS

We claim:

1. A blend of optical brighteners comprising (a) from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes; and (b) from 55 to 5 weight % of at least one
 5 bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, a coumarin based brightener, and mixtures thereof wherein said weight percents are based on the total weight of optical brighteners in said blend.

2. The optical brightener blend of claim 1 wherein mixture (a) comprises (i) from 25
 10 to 50 parts by weight of a first component selected from 4,4'-bis(benzoxazol-2-yl)stilbene and (ii) from 75 to 50 parts by weight of a second component selected from the group consisting of mono and di substituted benzoxazolyl stilbenes.

3. The optical brightener blend of claim 2 wherein component (ii) is represented by the formula




15

wherein $R_1 - R_4$ are independently selected from the group consisting of hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof.

4. The optical brightener blend of claim 3 wherein $R_1 - R_4$ are independently selected
 20 from the group consisting of hydrogen, a methyl group, an ethyl group, a tert-butyl group, a tert-octyl group and mixtures thereof.
5. The optical brightener blend of claim 4 wherein said component (ii) is selected from the group consisting of 4-(benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene, and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene.
- 25 6. The optical brightener blend of claim 1 wherein (b) is a bis(benzoxazolyl)naphthalene based brightener having the formula


-18-



wherein $R_5 - R_8$ are independently selected from the group consisting of hydrogen,
 an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon
 atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof.

7. The optical brightener blend of claim 6 wherein $R_5 - R_8$ are independently selected
 from the group consisting of hydrogen, a methyl group, an ethyl group, a tert-butyl
 group, a tert-octyl group and mixtures thereof.


8. The optical brightener blend of claim 1 wherein (b) is a bis(benzoxazolyl)thiophene
 based brightener having the formula



wherein $R_9 - R_{12}$ are independently selected from the group consisting of hydrogen,
 an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon
 atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof.

9. The optical brightener blend of claim 6 wherein $R_9 - R_{12}$ are independently selected
 from the group consisting of hydrogen, a methyl group, an ethyl group, a tert-butyl
 group, a tert-octyl group and mixtures thereof.
10. The optical brightener blend of claim 1 wherein (b) is a pyrazoline based brightener
 having the formula

-19-




wherein R_{13} - R_{15} are independently selected from the group consisting of hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxy group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms, a sulfonamido group and mixtures thereof.

5

11. The optical brightener blend of claim 10 wherein R_{13} - R_{15} are independently selected from the group consisting of hydrogen, a methyl group, an ethyl group, a tert-butyl group, a tert-octyl group and mixtures thereof.

12. The optical brightener blend of claim 1 wherein (b) is a coumarin based brightener having the formula

10



wherein R_{16} is selected from the group consisting of an organic group containing a triazine and triazole ring, R_{17} is selected from the group consisting of hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxy group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof.


15

13. The optical brightener blend of claim 1 wherein (a) is a mixture of first component (i) selected from 4,4'-bis(benzoxazol-2-yl)stilbene and a second component (ii) selected from the group consisting of 4-(benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene, and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene and (b) is selected from the group consisting of 2,5-bis(5-*t*-butylbenzoxazol-2-yl)thiophene, 3-phenyl-7-(2,3-naphthotriazol-2-yl)coumarin, 3-phenyl-7-(1,2-naphthotriazol-2-yl)coumarin, 3-phenyl-7-(benzotriazol-2-yl)coumarin and mixtures thereof.

20

-20-


14. An optically brightened polyolefin resin comprising a polyolefin and an effective amount of optical brightener blend admixed therein wherein said optical brightener mixture comprises (a) from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes comprising (i) from 25 to 50 parts by weight of a first component selected from 4,4'-bis(benzoxazol-2-yl)stilbene and (ii) from 75 to 50 parts by weight of a second component selected from the group consisting of mono and di substituted benzoxazolyl stilbenes represented by the formula



- wherein $R_1 - R_4$ are independently selected from the group consisting of hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxy group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof; and (b) from 55 to 5 weight % of at least one bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, a coumarin based brightener, and mixtures thereof wherein said weight percents of (a) and (b) are based on the total weight of optical brighteners in said mixture.
15. The optically brightened polyolefin resin of claim 14 wherein said polyolefin is selected from the group consisting of polyethylene, polypropylene, polybutylene, copolymers of said polyolefins and mixtures thereof.
16. The optically brightened polyolefin of claim 15 wherein said polyolefin is polyethylene and copolymers thereof having from 0.001 to 0.1 weight % of said optical brightener blend admixed therein, wherein said (ii) second component is selected from the group consisting of 4-(benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene, and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene and said (b) is selected from the group consisting of 2,5-bis(5-t-butylbenzoxazol-2-yl)thiophene, 3-phenyl-7-(2,3-naphthotriazol-2-yl)coumarin, 3-phenyl-7-(1,2-naphthotriazol-2-yl)coumarin, 3-phenyl-7-(benzotriazol-2-yl)coumarin and mixtures thereof.

-21-

17. A photoimaging material comprising a photoimaging support, a titanium dioxide pigment that is substantially free of silane coupling agents adjacent to said photoimaging support, and an optically brightened polyethylene resin having from 0.001 to 1.0 weight % of optical brightener blend admixed with said polyethylene, wherein said optical brightener mixture comprises (a) from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes comprising (i) from 25 to 50 parts by weight of a first component selected from 4,4'-bis(benzoxazol-2-yl)stilbene and (ii) from 75 to 50 parts by weight of a second component selected from the group consisting of mono and di substituted benzoxazolyl stilbenes represented by the formula



10

- wherein $R_1 - R_4$ are independently selected from the group consisting of hydrogen, an alkyl group having 1 to 15 carbon atoms, an alkoxyl group having 1 to 15 carbon atoms, an aryl group having from 6 to 15 carbon atoms and mixtures thereof; and (b) from 55 to 5 weight % of at least one bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, a coumarin based brightener, and mixtures thereof wherein said weight percents of (a) and (b) are based on the total weight of optical brighteners in said mixture.

18. The photoimaging material of claim 17 wherein said photoimaging support material is a cellulose containing material selected from the group consisting of paper, and modified cellulose materials selected from the group consisting of cellulose esters, cellulose ethers, nitrocellulose, viscose cellulose, microcrystalline cellulose, and microfibrillated cellulose.
19. The photoimaging material of claim 17 wherein (b) is selected from the group consisting of 2,5-bis(5-t-butylbenzoxazol-2-yl)thiophene, coumarin brightener (Leucopure EGM) and mixtures thereof.

25

-22-

20. The photoimaging material of claim 17 wherein from 0.01 to 0.5 weight % of said optical brightener mixture is admixed with said polyethylene resin.
21. A photoimaging material comprising a photoimaging support, a titanium dioxide pigment that is substantially free of silane coupling agents adjacent to said
5 photoimaging support, and an optically brightened polyethylene resin having from 0.001 to 1.0 weight % of optical brightener blend admixed with said polyethylene, wherein said optical brightener mixture comprises (a) from 45 to 95 weight % of a mixture of benzoxazolyl stilbenes comprising (i) from 25 to 50 parts by weight of a
10 first component selected from 4,4'-bis(benzoxazol-2-yl)stilbene and (ii) from 75 to 50 parts by weight of a second component selected from the group consisting of 4-(benzoxazol-2-yl)-4'-(5-methylbenzoxazol-2-yl)stilbene, and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene; and (b) from about 55 to about 5 weight % of at least one bis(benzoxazolyl)naphthalene based brightener, bis(benzoxazolyl)thiophene based brightener, a pyrazoline based brightener, a
15 coumarin based brightener, and mixtures thereof wherein said weight percents of (a) and (b) are based on the total weight of optical brighteners in said mixture.
22. The photoimaging material of claim 21 wherein (b) is selected from the group consisting of 2,5-bis(5-t-butylbenzoxazol-2-yl)thiophene, 3-phenyl-7-(2,3-naphthotriazol-2-yl)coumarin, 3-phenyl-7-(1,2-naphthotriazol-2-yl)coumarin,
20 3-phenyl-7-(benzotriazol-2-yl)coumarin and mixtures thereof.

INTERNATIONAL SEARCH REPORT

Int lional Application No
PCT/US 01/31112

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C08K5/00 C08L23/02 D06L3/12		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C08K D06L G03C G03F		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 791 680 A (HOECHST AG) 27 August 1997 (1997-08-27) claims 1-5	1,6-9;12
Y	examples 3,4,7,9-11 ---	1-22
Y	DATABASE WPI Section Ch, Week 198931 Derwent Publications Ltd., London, GB; Class E13, AN 1989-223764 XP002184230 & JP 01 159655 A (FUJII PHOTO FILM CO LTD), 22 June 1989 (1989-06-22) abstract --- -/--	1-22
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family		
Date of the actual completion of the international search 28 November 2001		Date of mailing of the international search report 11/12/2001
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Rose, E

INTERNATIONAL SEARCH REPORT

In International Application No
PCT/US 01/31112

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	PATENT ABSTRACTS OF JAPAN vol. 018, no. 630 (P-1835), 30 November 1994 (1994-11-30) & JP 06 242549 A (MITSUBISHI PAPER MILLS LTD), 2 September 1994 (1994-09-02) abstract ----	1-22
X	US 4 447 350 A (MARTINI THOMAS ET AL) 8 May 1984 (1984-05-08) claims 1-6 ----	1-9,12, 13
X	DE 33 13 332 A (HOECHST AG) 18 October 1984 (1984-10-18) claims 1-4 ----	1,10,11
X	US 4 129 412 A (GUNTHER DIETER ET AL) 12 December 1978 (1978-12-12) claim 1 example 1 ----	1
A	DE 15 94 855 A (FARBWERKE HOECHST AG) 13 May 1971 (1971-05-13) claims 1,2 ----	1-22
A	US 4 666 627 A (MEYER HANS R) 19 May 1987 (1987-05-19) claims 1,10,11,13,14 ----	1-22
A	US 4 508 784 A (GUGLIELMETTI LEONARDO) 2 April 1985 (1985-04-02) claims 1,19 ----	1-22
A	DE 38 18 986 A (CIBA GEIGY AG) 22 December 1988 (1988-12-22) claims 1,13,14 -----	1-22

INTERNATIONAL SEARCH REPORT

Information on patent family members

Initial Application No.
PCT/US 01/31112

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0791680	A	27-08-1997	DE 19607046 A1 BR 9701047 A CN 1263126 A EP 0791680 A2 JP 10001563 A SG 67373 A1 TW 422864 B	28-08-1997 15-12-1998 16-08-2000 27-08-1997 06-01-1998 21-09-1999 21-02-2001
JP 1159655	A	22-06-1989	NONE	
JP 06242549	A	02-09-1994	NONE	
US 4447350	A	08-05-1984	DE 3027479 A1 AT 7805 T AU 541954 B2 AU 7308881 A BR 8104599 A CA 1161208 A1 DE 3163976 D1 EP 0044996 A1 JP 57051758 A KR 8401761 B1 PH 18573 A ZA 8104904 A	04-03-1982 15-06-1984 31-01-1985 28-01-1982 06-04-1982 31-01-1984 12-07-1984 03-02-1982 26-03-1982 19-10-1984 12-08-1985 28-07-1982
DE 3313332	A	18-10-1984	DE 3313332 A1	18-10-1984
US 4129412	A	12-12-1978	DE 2629703 A1 AR 218257 A1 AT 465677 A AU 509035 B2 AU 2666177 A BE 856463 A1 BR 7704321 A CA 1088259 A1 CH 643420 A ,B CS 192581 B2 DD 132510 A5 DK 295077 A FR 2356761 A1 GB 1588447 A IE 45428 B1 IT 1080755 B JP 53005225 A NL 7707092 A ,B, PH 16589 A PL 199299 A1 PT 66755 A ,B RO 73275 A1 SE 7707613 A SU 1082331 A3 ZA 7703946 A	12-01-1978 30-05-1980 15-01-1983 17-04-1980 04-01-1979 04-01-1978 04-04-1978 28-10-1980 15-06-1984 31-08-1979 04-10-1978 03-01-1978 27-01-1978 23-04-1981 25-08-1982 16-05-1985 18-01-1978 04-01-1978 22-11-1983 24-04-1978 01-08-1977 21-06-1984 03-01-1978 23-03-1984 30-05-1978
DE 1594855	A	13-05-1971	DE 1594855 A1 NL 6818427 A ,B SE 361053 B	13-05-1971 01-07-1969 15-10-1973
US 4666627	A	19-05-1987	DE 3472105 D1	21-07-1988

INTERNATIONAL SEARCH REPORT

Information on patent family members

In International Application No
PCT/US 01/31112

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4666627	A	EP 0136259 A1 JP 60054372 A	03-04-1985 28-03-1985
US 4508784	A	02-04-1985	
		BR 8108052 A DE 3176183 D1 EP 0054511 A2 JP 1658816 C JP 2300147 A JP 3021539 B JP 1621645 C JP 2045662 B JP 57123263 A	21-09-1982 19-06-1987 23-06-1982 21-04-1992 12-12-1990 22-03-1991 09-10-1991 11-10-1990 31-07-1982
DE 3818986	A	22-12-1988	DE 3818986 A1 22-12-1988

